



Marbelite International Corporation

"We Make Concrete Beautiful"

Typical Physical Properties

	Unmodified Cement	Acrylic Modified Cement
Tensile Strength (PSI)		
28 Day Air Cure	235	855
28 Day Wet Cure	535	
Compressive Strength (PSI)		
28 Day Air Cure	2390	5720
28 Day Wet Cure	5795	
Flexural Strength(PSI)		
28 Day Air Cure	610	1890
28 Day Wet Cure	1070	
Shear Bond Adhesion(PSI)		
28 Day Air Cure	45 (A)	655 (C)
28 Day Wet Cure	185 (A)	
Impact Strength (IN LBS.)		
28 Day Air Cure	6	21
28 Day Wet Cure	7	

Caution:

This resin is not expected to be acutely toxic by single, oral, dermal, or inhalation exposure. It may be mild to moderate skin and eye irritants. It is suggested that these materials be washed from the skin with soap and water.