



## Marbelite International Corporation

"We Make Concrete Beautiful"

### Chemical and Stain Resistance of the Marbelite System

*H <sub>2</sub> SO <sub>4</sub> , 10 %	Intact; Unaffected
*Ca (OH) <sub>2</sub> , 10%	Intact; Unaffected
*NaOH, 10%	Intact; Unaffected
*Citric, 10%	Intact; Unaffected
*Lactic, 10%	Intact; Unaffected
*Gasoline	Intact; Unaffected
**Acid (10% w/w hydrochloric acid)	Intact; Unaffected
**Alkali (10% w/w sodium hydroxide)	Intact; Unaffected
**Mineral Spirits	Intact; Unaffected
**Methyl Alcohol	Intact; Unaffected
**Lubricating Oil	Intact; Unaffected
***NaOH, 10%	Intact; Unaffected
***Citric, 10%	Intact; Unaffected
***Lactic, 10%	Intact; Unaffected
***Gasoline	Intact; Unaffected

\*Immersion Time – 5 Minutes

\*\*Contact Time – 15 Minutes

\*\*\*Immersion Time – 7 Hours

#### Note:

In each case, the test chemical/staining substance was allowed to remain in contact with the surface of the Marbelite System for the specified time. After washing the test surface in running water, a visual examination was made of the surface.